

Specification Sheet for Bostik 1181 Adhesive

Trim and General Purpose Sprayable Adhesive

Stock Code ADB1181S20

Type:	Synthetic/rubber/resin.
Solvent:	Hydrocarbon/Ketone.
Flashpoint:	Below 0°C.
Colour:	Amber or red.
Viscosity:	Thin, sprayable.
Temperature Range:	Satisfactory between -23°C to 90°C dependant on bond line stress.
Bonding Range:	From 10 minutes to 2 hours at 25°C.
Coverage:	Approximately 4 m ² /L of bonded area dependant on surface porosity.
Cleaner:	Bostik No.2 Solvent.