

Specification Sheet for Bostik Triple 5 BSR

Laminating and General Purpose Adhesive

Stock Code ADB555N

Type:	Neoprene contact.
Solvent:	Hydrocarbon/Ketone mixture.
Flashpoint:	Below 0°C.
Solids Content:	Approx. 20%.
Colour:	Red.
Viscosity:	Sprayable grade, but due to high solids content may also be brushed or rolled.
Temperature Range:	-20°C to 150°C dependant on bond line stress.
Bonding Range:	10 – 60 minutes dependant on temperature and substrates bonded (contact) or up to 24 hours (heat activate).
Coverage:	2 – 5 m ² /L of bonded area dependant on surface porosity and application method.