

## Specification Sheet for Covertarp

### P.E. Tarpaulin Fabric

#### Stock Code PVCT

TESTS CONDUCTED		RESULTS (+/-5%)	TEST METHODS
AVERAGE WEIGHT		312 g/sq.m	ASTM D5216
COLOR		WHITE/WHITE	
ROLL SIZE		2X100M	
AVERAGE ROLL WEIGHT		66.45 KGS	
BASE FABRIC		12X10 PE WITH FOLDED YARN	
STRUCTURE		LDPP COATING+ HDPP WOVEN + LDPP COATING	
TENSILE STRENGTH	MD Warp	2,210 N	ASTM D5035
	CD Weft	1,746 N	
ELONGATION	MD Warp	19.5%	ASTM D5035
	CD Weft	21.0%	
TEARING STRENGTH	MD Warp	416 N	ASTM D4533
	CD Weft	405 N	

TESTS CONDUCTED		RESULTS (+/-5%)	TEST METHODS
AVERAGE WEIGHT		311 g/sq.m	ASTM D5216
COLOR		Olive Green/Olive Green	
ROLL SIZE		4X50M	
AVERAGE ROLL WEIGHT		70.04	
BASE FABRIC		12X10 PE WITH FOLDED YARN	
STRUCTURE		LDPP COATING+ HDPP WOVEN + LDPP COATING	
TENSILE STRENGTH	MD Warp	2,194 N	ASTM D5035
	CD Weft	1,746 N	
ELONGATION	MD Warp	19.0%	ASTM D5035
	CD Weft	22.0%	
TEARING STRENGTH	MD Warp	433 N	ASTM D4533
	CD Weft	418 N	