

Specification Sheet for Covertarp PVCT

Sample Description Weight: 316g/m² 12X10 WEAVE
Color: White/white
Composition: LDPE coating +HDPE woven scrim+ LDPE coating
Nominal Thickness: <1mm

ASTM G154	Method of test for textiles - Physical Test Determination of QUV of Textile Fabrics		
	Date of Testing	2021/5/30-2021/7/4	
	0.89 Watt/m ² , 340nm lamp and 850 hours		
	Normal condition	Specimen	MD - ASTM D5035
		1	2,192 N
		2	2,236 N
		3	2,302 N
		Average	2,243 N
	After test	Specimen	MD - ASTM D5035
		1	2,190 N
		2	2,233 N
		3	2,279 N
		Average	2,234 N
	Strength maintained	99.6%	
	Normal condition	Specimen	CD - ASTM D5035
		1	1,532 N
		2	1,623 N
		3	1,598 N
		Average	1,584 N
	After test	Specimen	CD - ASTM D5035
		1	1,522 N
		2	1,612 N
		3	1,579 N
		Average	1,571 N
	Strength maintained	99.2%	