



Prep G

Product

Simson Prep G has been developed as a black pretreatment for use on glass, not having a ceramic coating, in order to provide a UV-protecting coat, before applying special adhesives for bonding glass (also PMMA and PC) in the automotive, bus, ship and railway industries.

Applications

- Pretreatment of glass substrates without ceramic coating.
- Repair of damaged paint layers on metallic supports.

Method of use

The substrate should be clean, firm, dry and free of dust and grease. Cleaning of the substrates can be done with e.g. Simson Cleaner 14 or Simson Cleaner I. A small trial before application whether the cleaners will not attack the substrate is recommended. Keep the packaging of Prep G well closed until the moment of use. Prep G reacts with the humidity of the air. Shake bottle before use. Do not re-use a previously opened bottle. For the application of Prep G always use a clean brush, roller or felt applicator. The primer should be applied in one strike. Application temperature between +5°C and +30°C. Do not use when condensation is formed (high air humidity and cold substrates). Prep G should dry for at least 5 minutes. Apply the adhesive within 24 hours.

ADHESIVES AND SEALANTS

Prep G

Technical data

Total solids	ca. 22%	
Density	ca. 0.99 g/ml	
Dry time	> 5 minutes	(20°C/50% R.H.)
Flash point	-1°C	
Colour	smooth black liquid	
Packaging	30 ml and 250 ml bottle	

Coverage

The coverage of Simson Prep G is approximately 10 m² per litre.

Storage stability

Prep G can be stored for 9 months in an original, unopened container in a dry place at temperatures between +5°C and +30°C.

Further information

The following publication is available on request:

- Material Safety Data Sheets (MSDS)

UK

Bostik Ltd.
Stafford
Tel: +44 (0) 1785 27 27 27
Fax: +44 (0) 1785 22 26 65

France

Bostik S.A.
Paris
Tel: +33 (0) 1 74 96 91 18
Fax: +33 (0) 1 47 96 94 20

Germany

Bostik GmbH
Borgholzhausen
Tel: +49 (0) 54 25/8 01-0
Fax: +49 (0) 54 25/80 11 40

The Netherlands

Bostik B.V.
's-Hertogenbosch
Tel: +31 (0) 73 6 244 244
Fax: +31 (0) 73 6 244 344