

Specification Sheet for Roadmaster™ Lining

100% Polyester Walling and Headlining Fabric

Stock Code CPRL

Testing Items		Specification	Testing Result		Testing Methods (Standard)
Mass (gm/sqm)		250 ± 25	265		50cm*50cm/pcs
Thickness (mm)		1.5 ± 0.2	1.6		Thickness gauge
Tensile Strength (N/cm)		49 min	MD	85	TSL3610G-class4 (NWF)
			CD	89.2	
Elongation (%)		40 min	MD	56.7	TSL3610G-class4 (NWF)
			CD	70.5	
Tear Strength (N)		29.4 min	MD	57	TSL3610G-class4 (NWF)
			CD	54.8	
Taber abrasion resistance (Grade)		Grade 3 or better	Grade 3		TSL3610G-class4 (NWF)
Light resistance (Grade)	Discolouration	Grade 4 or better	Grade 4		TSL3610G-class4 (NWF)
	Fading	Grade 3 or better	Grade 4		
Colour fastness to abrasion (Grade)	Dry crocking	Grade 4 or better	Grade 4		TSL3610G-class4 (NWF)
	Wet crocking	Grade 4 or better	Grade 4		
Heat aging resistance		No abnormalities	No abnormalities		TSL3610G-class4 (NWF)
Humidity aging resistance		No abnormalities	No abnormalities		TSL3610G-class4 (NWF)
Water immersion shrinkage (%)		1 max.	0.1		TSL3610G-class4 (NWF)