

www.retwine.co.nz

Specification Sheet for Bradmill Outdoor Fabrics 10 300 200 XLP Superdux®

Tenting and General Purpose Polyester/Cotton Light-Weight Canvas

Stock Code CVBSD8

Finish: **XLP** Pigment coloured, waterproofed and rot proofed.

Yarn composition: 2 ply 65% polyester, 35% cotton, combed ring-spun yarn in both warp and weft.

Weave: Plain

Mass: 280 g/m² (8.3 oz/yd²) Nominal Loomstate:

> 345 g/m² (10.1 oz/yd²) XLP Proofed:

Width: 200 cm

Roll Length: 50 m

Typical Performance:

Strenath:

	Test Method	Warp	Weft
Breaking Force (N)	AS2001.2.3A	1840	1430
Tearing Force (N)	AS2001.2.10	65	45

Water resistance:

	Test method	XLP	CWR
Hydrostatic pressure (kPA)	AS2001.2.17	6.0	4.0
Cone leakage (ml)	AS2001.2.18	0	0

Shrinkage: Relaxation shrinkage (%): Warp: -2.5

Weft: +/-0.5

Relaxation shrinkage test results provide a good guide as to how the canvas will react to everyday use and are useful in determining the best way to cut and style products.

Colour Fastness:

	Test method	Dry/wet	XLP	CWR
Light fastness	AS2001.4.21	-	6-7	6
Bub footness	AS2001.4.3	Dry	3-4	4
Rub fastness	A32001.4.3	Wet	4	3-4

Total Colour Difference (compared to nominated standard): CMC 2:1 DE <1.0

