

Specification Sheet for Velcro® 0172 and 0119 Adhesives

0172: General Purpose Acrylic Self Adhesive

0119: High Performance Rubber-Based Adhesive Specially Formulated for Polypropylene and Polyethylene

Stock Codes FAVP / FAVODP

Specification		0172 Adhesive			0119 Adhesive		
Operating Temperature		-28°C to 107°C			-40°C to 85°C		
Bond strength		Moderate. Full bond strength achieved in 24 hrs.			Moderate. Full bond strength achieved in 24 hrs.		
		19mm	25mm	50mm	19mm	25mm	50mm
Colour	Black	✓	✓	1	Х	1	1
	White	\checkmark	 Image: A set of the set of the	~	Х	1	~
	Beige	\checkmark	\checkmark	1	Х	Х	Х

Packaging:

25 m rolls of either hook or loop.

Hook and Loop Closure Performance:

HOOK AND LOOP CLOSURE PERFORMANCE										
WHEEL CYCLE LIFE IN PEEL MODE.	SHEAR STRENGTH LENGTH WISE. P.S.I. AVERAGE	SHEAR STRENGTH WIDTH WISE. P.S.I. AVERAGE	CURVED SHEAR ON 41/2" RADIUS P.S.I. AVERAGE	TENSION OR LATCHING EFFECT P.S.I. AVERAGE	PEEL STRENGTH LENGTH WISE. P.I.W. AVERAGE					
				*	*					
HIGH	14	10.5	28.0	6.5	1.2					

For Best Results:

- Surface should be clean, dry and free of oils.
- Use clean wiping material with isopropyl alcohol (rubbing alcohol) to free surface of contaminates and allow to dry.
- Peel release liner from back of tape and apply. Be careful not to touch adhesive with your fingers.
- To maximise adhesive performance, substrate and tape should be applied in conditions of 18-24°C.
- Allow 24 hours for full bond strength.

Auckland: 7 Arthur Brown Place, Mt Wellington 1060 • PO Box 11 2230, Penrose, Auckland 1642 Christchurch: 15 Watts Road, Sockburn 8042 • PO Box 11 132, Sockburn, Christchurch 8443

